

Development of an Experimental Home Bleaching Agent Containing Chitosan Nanoparticles Loaded with Gypsophila arrostii Extract

Gypsophila Arrostii Ekstresi Yüklü Kitosan Nanopartikülleri İçeren Deneysel Ev Tipi Beyazlatma Ajanının Geliştirilmesi

Selinsu Öztürk¹, Pınar Yılmaz Atal^{2,3}, Bahar Gök^{4,5}, Yasemin Budama-Kılınc^{3,4}, Elif Alkan^{2,3}, Dilek Tağtekin^{2,3}, Şeyma Ulusoy⁶, Murat Kartal^{6,7}

¹ Marmara University Institute of Health Sciences, Department of Restorative Dentistry, Istanbul, Türkiye.

² Marmara University Faculty of Dentistry, Department of Restorative Dentistry, Istanbul, Türkiye.

³ Health Biotechnology Joint Research and Application Center of Excellence, Istanbul Türkiye.

⁴ Yıldız Technical University Faculty of Chemical and Metallurgical Engineering, Bioengineering Department, Istanbul, Türkiye.

⁵ Istanbul Technical University, ARI Teknokent, Raymare Biotechnology Inc., Istanbul, Türkiye.

⁶ Department of Pharmacognosy, Faculty of Pharmacy, Bezmialem Vakıf University, Istanbul, Türkiye.

⁷ Phytotherapy Research Center, Bezmialem Vakıf University, Istanbul, Türkiye.

ABSTRACT

Objectives: Peroxide alternative agents are currently being developed to provide a safe and effective tooth whitening treatment, given the potential for these agents to affect hard dental tissue. In this study, it is aimed to produce an experimental home whitening gel containing Gypsophila arrostii extract (GE) loaded chitosan nanoparticles with controlled release property.

Materials and Methods: GE was prepared in two different ways using water or ethanol, and the saponin amounts of both extracts were measured using gravimetric analysis methods. GE-loaded chitosan nanoparticles (GECNPs) prepared by the ionic gelation method were investigated in terms of size, zeta potential, polydispersity index (Pdl), encapsulation efficiency, and release profile. The significance level was set at $p < 0.05$.

Results: The water-based extract was preferred for encapsulation due to its statistically significantly higher percentage of saponin content ($45.38 \pm 3.050396\%$) ($p=0.335$). According to the characterization results, GECNPs were 651 ± 8.34 nm in average particle size, 0.242 ± 0.02 Pdl, and 44.7 ± 0.21 mV zeta potential. Encapsulation efficiency was determined as $97.41 \pm 3.02\%$. GE release from GECNP was calculated as $94.11 \pm 4.03\%$ at 48 h, and the drug release rate increased by adding peroxides.

Conclusions: The controlled release system of Gypsophila arrostii extract-loaded CNPs was successfully synthesized to develop an experimental home-bleaching gel as an alternative and promising approach.

Keywords: Gypsophila arrostii, saponin, chitosan, controlled release system, tooth bleaching

ÖZ

Amaç: Diş sert dokusu üzerindeki potansiyel yan etkileri nedeniyle sağlıklı ve etkili diş beyazlatma tedavisi için peroksit alternatifleri ajanlar geliştirilmektedir. Bu çalışmanın amacı kontrollü salım özelliğine sahip çöven otu (Gypsophila arrostii) ekstresi yüklü kitosan nanopartikülleri içeren deneysel ev tipi beyazlatma jeli oluşturmaktır.

Gereç ve Yöntemler: Gypsophila arrostii ekstresi (GE) su veya etanol kullanılarak iki farklı şekilde hazırlanmıştır ve her iki ekstrenin saponin miktarı gravimetrik analiz yöntemleri kullanılarak ölçülmüştür. İyonik jelleşme yöntemi kullanılarak hazırlanan GE yüklü kitosan nanopartikülleri; partikül boyutu, zeta potansiyeli, polidispersite indeksi (Pdl), enkapsülasyon etkinliği ve salım profili açısından incelenmiştir.

Bulgular: Su bazlı GE, istatistiksel olarak anlamlı derecede daha yüksek saponin içeriği ($45,38 \pm 3,050396$) ($p=0,335$) nedeniyle enkapsülasyon için tercih edilmiştir. GE yüklü kitosan nanopartiküllerinin ortalama boyutu $651 \pm 8,34$ nm, Pdl değeri $0,242 \pm 0,02$ ve zeta potansiyeli $44,7 \pm 0,21$ mV olarak ölçülmüştür. Enkapsülasyon etkinliği $97,41 \pm 3,02$ olarak belirlenmiştir. GECNP'den GE salımının 48 saatte $94,11 \pm 4,03$ 'e ulaştığı ve salım hızının peroksitlerin ilavesiyle arttığı gözlemlenmiştir.

Sonuç: Kontrollü salım sistemi özellikli GE yüklü CNP'lerin sentezi, gelecek vaat eden alternatif bir yaklaşım olarak deneysel bir ev tipi beyazlatma jeli geliştirmek amacı başarı ile gerçekleştirilmiştir.

Anahtar Kelimeler: Kelimeler: Çöven otu, saponin, kitosan, kontrollü salım sistemi, diş beyazlatma

Corresponding Author

Selinsu Öztürk (✉)
selinsuozturk@marun.edu.tr

Article History

Submitted 23.11.2024

Revised 03.12.2024

Accepted 23.01.2025

Published 30.04.2025

How to cite this article: Öztürk, S., Atal P, Y., Gök, B., Kılınc, Y., B., Alkan, E., Tağtekin, D., Ulusoy, Ş., Kartal, M. Development of an Experimental Home Bleaching Agent Containing Chitosan Nanoparticles Loaded with Gypsophila arrostii Extract. European Journal of Research in Dentistry. *European Journal of Research in Dentistry*, 2025;9(1): 1-8. DOI: <http://dx.doi.org/10.29228/erd.86>



INTRODUCTION

Tooth bleaching, a well-established and effective aesthetic procedure in dentistry, provides a more conservative approach to whitening vital teeth than treatments such as crowns or ceramic veneers (Meireles et al., 2008). The most commonly used components are carbamide peroxide (CP) and hydrogen peroxide (HP), each with specific concentrations for different techniques. The treatment can be performed either in the office or at home (Haywood, 1997). In recent years, home bleaching has become increasingly popular among whitening therapies due to the reduced time spent in the clinic compared to office-based treatments and its lower peroxide content, offering an effective whitening with long-term permanence of the color after the treatment. The most prevalent method of application remains the use of hydrogen peroxide gels with a concentration of up to 6% or carbamide peroxide gels with a concentration of up to 16% for approximately two weeks with a custom tray under the supervision of a dentist (De Geus et al., 2016). Despite its popularity, some adverse effects have been documented. These include tooth sensitivity, decreased bond strength and micro-hardness values, a slight change in surface roughness, and alterations in enamel and dentin mineral content. Although these alterations are regarded as insignificant or reversible, the treatment has been demonstrated to diminish the concentration of calcium and phosphorus within the tooth structure (Pini et al., 2022). Furthermore, carboxy polymethylene, or carbopol, which is frequently utilized as a carrier in CP gels, has also been demonstrated to reduce enamel microhardness (Rodrigues et al., 2005). It would be advantageous to develop a more efficient tooth bleaching method that causes minimal side effects on the enamel, pulp, and oral mucosa while avoiding contraindications. Nowadays, there is a growing trend to turn to natural materials for teeth whitening, as seen in many other areas, and the literature discusses several natural alternatives to peroxide bleaching that can produce oxidative reactions and effectively remove stains without adverse effects (Gopinath et al., 2013; Münchow et al., 2016). Therefore, developing new tooth-bleaching agents based on natural products with minor adverse effects and comparable esthetic results would be beneficial.

Saponins are non-volatile, surface-active compounds that are distributed in nature and are primarily found in the plant kingdom (Oleszek, 2002). Due to their foaming properties, saponins are employed in manufacturing cosmetics, detergents, and soaps. Saponins are also responsible for several other significant functions, including providing antimicrobial, antioxidant, and analgesic properties. A diet high in saponins has been demonstrated to be an effective method for preventing dental caries ((Jyothi & Seshagiri, 2012; Kareem et al., 2022; Timilsena et al., 2023). In addition, saponins derived from various plant sources have been widely used in herbal toothpaste formulations. Research has shown that their antibacterial and antiplaque effects, combined with their ability to promote oral hygiene, make them valuable ingredients in the prevention of dental issues.

Several studies have explored the potential of saponins in whitening teeth and preventing cavities, making them a natural and effective choice for those seeking alternative oral care solutions (Oluwasina et al., 2019; Oluwasina et al., 2023; Paul et al., 2020; Sugianti, 2012).

Gypsophila arrostii Guss., a member of the *Gypsophila* genus within the Caryophyllaceae family, is renowned for its triterpene saponins, which are present in its roots. Its notable phytochemical content makes it a promising subject for further study. (Davis et al., 1984); (Arslan et al., 2013). Gypsogenin represents the most prevalent basic structure of saponins isolated from the *Gypsophila* genus. Additionally, quillaic acid and gypsogenic acid are also present in lower concentrations (Arslan et al., 2013). *G. arrostii* is one of the five most utilized *Gypsophila* species in Türkiye (Baytop, 1999). It has been traditionally employed for its diuretic and expectorant activities (Özçelik & Yıldırım, 2011). It is a significant species in the pharmaceutical industry, serving as the primary source of saponins in vaccine adjuvants (Arslan & Cenzano, 2021). Moreover, *G. arrostii* is utilized to produce tahini halva, a significant ingredient in the Turkish food industry (Arslan, 2017). It serves as an emulsifier, facilitating the combination of sugar and sesame oil, bleaching the product's color, and enhancing its volume. Additionally, gypsophila species are employed in the cosmetic industry due to their gentle cleansing, soothing, and anti-inflammatory properties. Furthermore, they are known to enhance the penetration of other skincare ingredients (Bezerra et al., 2018). Additionally, reports indicate that the species is used in bleaching agents due to its saponin content (Guo et al., 2022). The synergistic effect of saponin compounds and their free radical neutralizing activity may play a significant role in their bleaching properties (Kang et al., 2024). An in vitro study investigating the effects of *Hibiscus Sabdariffa* extract on discolored teeth demonstrated that its saponin content contributed to whitening efficacy (Sugianti, 2012). Based on these findings, the saponin content of *G. Arrostii* extract was utilized to evaluate its potential bleaching properties in the present study. Nevertheless, there is a lack of studies in the literature evaluating the potential use of the *Gypsophila* genus in dentistry.

Chitosan, a natural polymer produced due to the deacetylation of chitin obtained from the shell of arthropods, acts as a thickener and carrier with its film-forming properties. It is known to protect the tooth from erosion and demineralization by acting as a stable barrier under enamel or dentin (Guo & Gemeinhart, 2008). Due to its biocompatible, bioadhesive, bioactive, and non-toxic properties, chitosan is frequently preferred in nanoparticle production (Peniche & Peniche, 2011). Nanoparticles (NPs) formed with chitosan with ionic cross-link structure have the advantages of prolonged release of drugs, protection against enzymatic degradation, and biodegradability (Sun et al., 2010). Concerns regarding the biocompatibility and toxicity of natural compounds present a significant challenge in their use; however, encapsulating plant compounds in polymeric nanoparticles helps to minimize potential adverse effects and increase bioavailability

(Patra et al., 2018). Encapsulation protects sensitive components and ensures a controlled release of active substances. Controlled drug release ensures that the encapsulated drug is delivered to the correct site, maintaining the appropriate amount of the drug in the target tissue while minimizing adverse side effects. Controlled release systems offer a number of advantages, including enhanced efficacy, high stability against enzymatic and other forms of degradation of encapsulated or immobilized components, reduced toxicity, and simplified application (Aydın & Ünlüel, 2021). Considering all this information, in the present study, experimental bleaching gels containing a controlled release system of chitosan loaded with *G. arrostii* extract (GE) were developed to minimize the potential side effects of whitening treatment and to provide an effective and stable whitening. The ionic gelation method was used in the synthesis of GE-loaded chitosan nanoparticles (GECNPs). Encapsulation capacity is essential for effective and long-term release in controlled release systems (Egil et al., 2020). Therefore, the encapsulation efficiency (EE) of GECNPs was determined in our study. The average particle size (Z-Ave), multiple distribution index (Pdl), and Zeta potential (ZP) values were analyzed, and the optimum nanoparticle was determined. *In vitro* release properties were also investigated.

MATERIALS AND METHODS

The materials utilized in the study are presented in Table 1.

Table 1. Materials used in the study

Material	CAS no.	Manufacturer
Chitosan (75-85% deacetylated, low molecular weight)	9012-76-4	Sigma-Aldrich (St. Louis, MO, USA)
Sodium tripolyphosphate	7758-29-4	
Diethyl ether	60-29-7	
Ethanol	64-17-5	
<i>n</i> -Butanol	71-36-3	
Sodium chloride	7647-14-5	
Hydrogen peroxide (30%)	7722-84-1	
Carbamide peroxide (97%)	124-43-6	Merck
Acetic acid	64-19-7	
<i>G. arrostii</i> roots*	-	

**G. arrostii* which is one of the five widely distributed and most used *Gypsophila* species in Türkiye, was purchased from Fitovizyon Doğal ve Sağlıklı Yaşam Ind. Trade Co. Ltd. (Istanbul, Türkiye) and identified by Prof. Dr. Murat Kartal. A voucher specimen was deposited at the Bezmialem Phytotherapy Research Center.

Preparation of GE

Two different extracts were prepared using the roots of *G. arrostii*. In Beaker A, 600 mL of water was added to 150 g of *G. arrostii* root. In Beaker B, 600 mL of 50% ethanol (EtOH) was added to 150 g of *G. arrostii* root. The two different mixtures were stirred in a magnetic stirrer at 50

°C, and 200 rpm for 4 hours. The extracts were filtered through filter paper and kept in a fume hood until dry. The dry extracts were ground with a grinder to a fine powder (Fig. 1).




Figure 1. Preparation of GE

a. Preparation of beakers, b. Stirring in a magnetic stirrer, c. Filtering through filter paper, d. Drying in fume hood, e. Grinding with a grinder

Saponin Measurement

The saponin content was determined using gravimetric methods (Arwani et al., 2019). 20 mL of 20% ethanol was added to 2 g of dry *G. arrostii* extract in a conical flask. 10 mL diethyl ether was added to the concentration in a 100 mL separatory funnel and shaken vigorously, from which the ether layer was discarded, and the aqueous layer was recovered. 20 mL *n*-butanol was added and extracted twice with 5 mL of 5% sodium chloride. After removing the sodium chloride layer, the remaining solution was heated in a water bath for 30 min, transferred into a beaker, and then dried in an oven to a constant weight. The saponin content was calculated as a percentage:

Spectrophotometric Analysis of GE

Seven distinct concentrations (7.8125, 15.625, 31.25, 62.5, 125, 250, and 500 µg/mL) were prepared, and their absorbance values were measured with a UV spectrophotometer to obtain a calibration curve which was subsequently utilized to determine the EE and analyze the *in vitro* release profile.

Preparation of GECNPs

Synthesis of GECNPs was carried out using the ionic gelation technique. Chitosan (3% w/v) was dissolved in water containing 1.5% (v/v) acetic acid solution and stirred on a magnetic stirrer (Daihan-Digital Magnetic Stirrer, Korea) for 24 h. 25 mg of sodium tripolyphosphate (TPP) was dissolved in 50 mL of distilled water. 10 mg of dry extract was dissolved in 1 mL of distilled water and added to the TPP solution. Then, after stirring at 250 rpm, it was mixed with chitosan solution and sonicated with 70 W energy for 5 minutes (Kaymak et al., 2024).

Preparation of Peroxide Based Experimental Bleaching Gels

100 mL solution of *Gypsophila* extract-loaded chitosan nanoparticles were mixed with HP at specified proportions to obtain a 6% HP experimental bleaching gel, while CP was mixed at specified proportions to obtain a 16% CP experimental bleaching gel.

Dynamic Light Scattering (DLS) Analysis

The Zetasizer Nano ZS (Malvern Instruments, England) device was used to measure Z-Ave, Pdl, and ZP of the produced chitosan-controlled release system. The particles were placed in a transparent cuvette, and measurements were taken with a 4.0 mV He-Ne laser (633 nm) at 25°C. Each sample was prepared by diluting it with water at a ratio of 1:10. The Z-Ave, Pdl, and ZP values of the samples were calculated by taking the average of three measurements.

Encapsulation Efficiency (EE)

5 mg of GECNPs were dissolved in 10 mL ethanol and sonicated in an ultrasonic bath for 30min. The quantity of encapsulated GE was calculated from the absorbance value obtained from the calibration curve using Equation 1.

$$\text{Encapsulation efficiency(\%)} = \frac{\text{Total amount of loaded GE}}{\text{Initial amount of loaded GE}} \times 100 \quad (1)$$

In vitro Release Profile

The *in vitro* release profile of GECNPs, GECNPs-HP, GECNPs-CP, and GE (as a control group) was determined using the membrane diffusion technique. A total of 1 mg of GECNPs were suspended in 1 mL of distilled water and placed on dialysis membranes. The release was conducted in 100 mL of PBS (pH 6.5) in a shaking water bath set at 25 °C room temperature at 120 rpm. At the designated time intervals (0.5, 1, 1.5, 2, 2.5, 3, 4, 5, 6, 24, and 48 h), 1 mL sample was taken from the release medium and replaced with an equal volume of buffer to maintain a constant volume in the release medium. Measurements were performed with a UV-Vis spectrophotometer (Shimadzu, UV-1280, Japan), and the amount of GE in the sample was calculated according to the standard curve Equation 2.

$$\text{Release (\%)} = \frac{\text{Released amount of GE}}{\text{Total amount of GE}} \times 100 \quad (2)$$

Statistical Analysis

Data were analyzed with IBM SPSS v23, using Shapiro-Wilk and Independent sample t-test; the significance level was taken as $p < 0.05$. Additionally, the results are expressed as the mean \pm standard deviation derived from three independent measurements.

RESULTS

Gravimetric Total Saponin Determination

The total weights of the *G. arrostii* root extracts prepared with 50% ethanol and 100% water were 45.6000 g and 42.8320 g after drying. Percentage of total saponin amounts determined gravimetrically from 2 g samples ($n=3$) of dried extracts are given in Table 2. A statistically significant difference was observed between ethanol and water-based extracts (0,035). The mean saponin content of the GEs prepared using ethanol was determined to be $39.83 \% \pm 0.2211$, whereas the GEs produced with water exhibited a higher saponin concentration of $45.38 \% \pm 3.0504$. According to these results, based on the saponin yield in dried 50% ethanol and 100% water extracts, the saponin yields of the *G. arrostii* roots were calculated as 12.1083 % and 12.9581 %, respectively.

Table 2. Percentage of total saponin amounts

Preparation conditions	n	g/2g	%	Mean % \pm SD	P
50 % EtOH	1	0.8000	40.0000	39.83 % \pm 0.2211	0,035
	2	0.7916	39.5800		
	3	0.7982	39.9100		
100 % H ₂ O	1	0.9715	48.5750	45.38 % \pm 3.0504	
	2	0.8499	42.4975		
	3	0.9015	45.0750		

Nanoparticle Characterization

Evaluation of Average Size, Polydispersity Index, and Zeta Potential

In this study, physicochemical properties such as Z-Ave, Pdl, and ZP value of GECNPs were determined according to DLS analysis. The results of the blank CNPs and GECNPs are presented in Table 3. According to the results, the blank chitosan-controlled release system has a Z-Ave of 1499 ± 46.67 nm, Pdl of 0.186 ± 0.12 , and ZP value of 43.8 ± 1.56 mV. GECNPs have a Z-Ave of 651.3 ± 8.34 nm, a Pdl of 0.242 ± 0.02 , and a ZP value of 44.7 ± 0.21 mV.

Table 3. Dynamic light scattering analysis results of blank CNPs and GE-CNPs

Samples	Average Particle Size (nm)	Polydispersity Index	Zeta Potential (mV)
Blank CNPs	1499 ± 46.67	0.186 ± 0.12	43.8 ± 1.56
GECNPs	651.3 ± 8.34	0.242 ± 0.02	44.7 ± 0.21

Encapsulation Efficiency

The EE of GECNPs was calculated as $97.41 \% \pm 3.02$ using the calibration curve given in Fig. 2.




Figure 2. The calibration curve of GE.

In vitro release study

The *in vitro* release graph of GECNPs was plotted as time and % amount of release (Fig. 3). The experimental groups demonstrated varying release profiles. GE release from GECNP reached $94.11\% \pm 4.03$ at 48 hours, while in the GECNP - 6% H₂O₂ group, it was $89.83\% \pm 2.01$ at 3 hours, and in the GECNP-16% CP group, it was $88.40\% \pm 4.30$ at 24 h. In comparison, the release of free GE was nearly complete ($92.68\% \pm 2.05$) within 5 h.




Figure 3. Controlled release graph of GE, GECNPs, and GECNPs with different components (HP, CP)

DISCUSSION

Nanoparticles can enhance product quality by incorporating various functional groups. As a result, nano products are extensively utilized in different industrial sectors, including medicine and dentistry. Chitosan exhibits distinctive characteristics, including biocompatibility, biodegradability, antimicrobial properties, and analgesic effects (Arnaud et al., 2010).

Chitosan nanoparticles prepared with TPP offer significant stability and don't require the use of external stabilizing agents or cross-linkers (Khan et al., 2016). Chitosan has already been incorporated into bleaching gels and has demonstrated no interference with their whitening effectiveness (Kolsuz Ozcetin & Surmelioglu, 2020; Pini et al., 2022). However, its potential to reduce the side effects of bleaching remains uncertain. Plant compounds

are encapsulated in polymeric nanoparticles to minimize potential side effects (Patra et al., 2018). In the light of all this information, chitosan was used to encapsulate GE and increase its bioavailability. In the present study, it was decided to utilize *G. arrostii* due to its high saponin content and obtain concentrated dried extracts with even higher saponin contents. Previously published studies have revealed that the roots of *G. arrostii* contain 11-22 % of total saponins (Battal et al., 2003; Koyuncu et al., 2008). According to the findings of our study, based on the saponin yield in dried 50 % EtOH and 100 % H₂O extracts, the saponin yields of the *G. arrostii* roots were calculated as 12.1083 % and 12.9581 %, respectively, which makes apparent that the roots we have used meet the criterion of having saponin 11-22 %. When we calculated the percentage of saponin content for both the 50% ethanol-based and the water-based dried and concentrated extracts, as presented in Table 2, the water-based extract was preferred for encapsulation due to its statistically significantly higher percentage of saponin content ($45.3800 \pm 3.0504\%$) ($p=0.035$).

Dynamic light scattering is commonly used to determine the hydrodynamic dimensions of nanoparticles, providing various advantages in nanoparticle sizing (Egil et al., 2020). In our study, Z-Ave, PDI, and ZP values of GECNPs were measured based on DLS principles. According to the results in Table 3, CNPs have a 1499 nm Z-Ave, 0.186 PDI, and 43.8 mV ZP value. However, GECNPs had a 651.3 nm Z-Ave, 0.242 PDI, and 44.7 mV ZP value (Table 3). According to the findings, loading CNPs with the extract decreased the Z-Ave, and increased the PDI, and the ZP value. Various parameters, including the synthesis conditions, the component mixing ratios, and the densities of extracts affect the size of the NPs (Egil et al., 2020). Weak and/or electrostatic interactions between the polymer and the plant extract chemical groups may contribute to the size variations seen in drug-loaded NPs (Manne et al., 2020). In the present study, the increase in particle size is attributed to the high chitosan content, while the inclusion of GE leads to a decrease in the size of the NPs. NPs are defined as particles smaller than 100 nm (Borm et al., 2006; Dowling, 2004). However, the size of polymeric NPs can range from 10 to 1.000 nm, making them suitable for a variety of applications (Gheffar et al., 2021; Hamzaoui & Laraba-Djebari, 2021; Ni et al., 2021; Roberts et al., 2020). The PDI value reflects the homogeneity of nanoparticle size, with a PDI value of 0.2 or lower indicating a more uniform distribution of nanoparticles (Rajamanickam & Manju, 2023). Neuroprotective flavonoid-loaded CNPs synthesized by Soltanzadeh et al. and myricetin-loaded chitosan nanoformulations synthesized by Upadhyay et al. had PDI values of 0.260 ± 0.015 and 0.272 ± 0.02 respectively (Soltanzadeh et al., 2021; Upadhyay et al., 2023). While the blank CNPs obtained in our study showed a uniform distribution, GECNPs demonstrated similarities with findings reported in the literature. The zeta potential allows us to assess the surface charge and stability of a nanostructure; ZP values greater than ± 30 mV indicate a high level of stability in the nanoparticles. (Simunkova et al., 2009). Based on our results, the ZP value of the

synthesized empty CNPs and GECNPs was above +30 mV, demonstrating good stability. The slight increase in the ZP value of GECNPs may be ascribed to the plant extract enhancing the number of positively charged groups on the surface of the nanoparticles (Manne et al., 2020).

Encapsulation is an essential strategy for stabilizing molecules and enhancing their efficacy. Hence, it is crucial to calculate and measure EE when preparing NPs (Shen et al., 2017). In the present study, the EE value was $97.41 \pm 3.02\%$. This value is in accordance with those reported in previous studies. Egil et al. prepared Epilobium extract (EPE) loaded chitosan nanoparticles, reporting an EE of 92.46% (Egil et al., 2020). Similarly, Khan et al. synthesized chitosan nanoparticles loaded with Curcumin, indicating that the EE was determined to be 85% (Khan et al., 2016).

In vitro release kinetics are critical as they indicate a molecule's pharmacokinetic and pharmacological behavior *in vivo* (Abdelkader et al., 2020). *In vitro* release studies were conducted using the membrane diffusion technique and monitored for 48 h, pH adjusted 6.5 to mimic the *vivo* conditions in the oral cavity accurately. In the present study, $94.11 \pm 4.03\%$ of the free GE loading was released from GECNPs within 48 hours. Similarly, Egil et al. reported that 96.04 % of EPE was released at pH 6.5 within the same 48-hour period (Egil et al., 2020). In the peroxide-based groups (GECNP-HP, GECNP-CP), it was found that the addition of peroxides accelerates GE release from GE-CNPs. In the presence of 6% HP and 16% CP, the release was $89.83 \pm 2.01\%$ at 3 hours and $88.40 \pm 4.30\%$ at 24 hours, respectively. This acceleration may be attributed to the acidic pH of HP and CP, as well as the pH-responsive properties of chitosan under slightly acidic conditions.

The European Scientific Committee on Consumer Products (SCCP) has indicated that tooth bleaching agents containing hydrogen peroxide ranging from 0.1% to 6.0% or equal hydrogen peroxide-releasing agents are considered safe when used under the guidance of a dentist (Affairs, 2008). Home bleaching gels can be applied to the enamel surface for a maximum of 1.5 and 6 hours, respectively, depending on the H₂O₂ or CP concentration they contain, and it is known that the effectiveness of the gels continues within the tooth structure even after the application period. So, accelerated extract release can be considered an advantage of whitening procedures.

CONCLUSION

In accordance with the *in vitro* findings, the GECNP formulation exhibited favourable physicochemical characteristics with regard to particle size, PDI, and zeta potential. GE was successfully encapsulated within CNPs. The incorporation of peroxides resulted in an accelerated release profile. Consequently, the developed controlled release system of GECNPs represents a promising potential agent for tooth bleaching. However, further studies are necessary to evaluate the potential cytotoxicity and assess its effects on dental hard tissues.

Acknowledgments

This study was supported by the Scientific Research Projects Coordination Unit of Marmara University under grant number 11078.

Conflicts of Interest

The authors have no financial interest in any companies or products mentioned in this article.

Ethical Approval

Not applicable.

REFERENCES

1. Abdelkader A, Fathi HA, Hamad MA, Elsabahy M. Nanomedicine: a new paradigm to overcome drug incompatibilities. *J Pharm Pharmacol*. 2020 Oct;72(10):1289-1305.
2. American Academy on Pediatric Dentistry Council on Clinical Affairs. Policy on dental bleaching for child and adolescent patients. *Pediatr Dent*. 2008-2009;30(7 Suppl):61-3.
3. Arnaud TM, de Barros Neto B, Diniz FB. Chitosan effect on dental enamel de-remineralization: an *in vitro* evaluation. *J Dent*. 2010 Nov;38(11):848-52.
4. Arslan I. A new acylated and oleanane-type triterpenoid saponin from *Gypsophila arrostii* roots. *Int J Food Prop*. 2017;20(3):507-13.
5. Arslan I, Celik A, Melzig MF. Nebulosides A-B, novel triterpene saponins from underground parts of *Gypsophila arrostii* Guss. var. *nebulosa*. *Bioorg Med Chem*. 2013;21(5):1279-83.
6. Arslan I, Cenzano AM. Characterization of triterpene saponins from *Gypsophila arrostii* by electrospray ionization ion trap multiple-stage mass spectrometry. *Rev Bras Farmacogn*. 2021;31(1):107-11.
7. Arwani M, Wijana S, Kumalaningsih S. Nutrient and saponin content of *Moringa oleifera* leaves under different blanching methods. In: International Conference on Green Agro-industry and Bioeconomy; 2018 Sep 18-20; Universitas Brawijaya, East Java, Indonesia. *IOP Conf Ser Earth Environ Sci*. 2019;230:012042. doi: 10.1088/1755-1315/230/1/012042.
8. Aydın Ö, Ünlüel İ. Enkapsülasyon teknikleri ve kontrollü salım. *Avr Bilim ve Teknol Derg*. 2021; 32:640-8.
9. Velioglu YS, Sarı F, Battal H. Çöven ekstraktı üretimi üzerine bir araştırma. *Anadolu Univ Sci Technol J*. 2003;4(1):75-84.
10. Baytop T. Türkiye'de bitkiler ile tedavi: geçmişte ve bugün. *Nobel Tıp Kitabevleri*; 1999.
11. Bezerra KGO, Rufino RD, Luna JM, Sarubbo LA. Saponins and microbial biosurfactants: Potential raw materials for the formulation of cosmetics. *Biotechnol Prog*. 2018;34(6):1482-1493. doi: 10.1002/btpr.2682. Epub 2018 Jul 27.
12. Davis P, Davis PH, Mill RR, Tan K. *Flora of Turkey and the East Aegean Islands*. Edinburgh: Edinburgh University Press; 1984.

13. de Geus JL, Wambier LM, Kossatz S, Loguercio AD, Reis A. At-home vs In-office Bleaching: A Systematic Review and Meta-analysis. *Oper Dent.* 2016 ;41(4):341-56.
14. Egil AC, Ozdemir B, Gok B, Kecel-Gunduz S, Budama-Kilinc Y. Synthesis, characterization, biological activities and molecular docking of *Epilobium parviflorum* aqueous extract loaded chitosan nanoparticles. *Int J Biol Macromol.* 2020;161:947-957.
15. Gopinath S, James V, Vidhya S, Karthikeyan K, Kavitha S, Mahalaxmi S. Effect of bleaching with two different concentrations of hydrogen peroxide containing sweet potato extract as an additive on human enamel: An in vitro spectrophotometric and scanning electron microscopy analysis. *J Conserv Dent.* 2013 ;16(1):45-9.
16. Guo C, Gemeinhart RA. Understanding the adsorption mechanism of chitosan onto poly(lactide-co-glycolide) particles. *Eur J Pharm Biopharm.* 2008 ;70(2):597-604.
17. Guo N, Bai Y, Huang X, Liu X, Cai G, Liu S, Guo Y, Gong J. Comparison of the Saponins in Three Processed American Ginseng Products by Ultra-High Performance Liquid Chromatography-Quadrupole Orbitrap Tandem Mass Spectrometry and Multivariate Statistical Analysis. *Int J Anal Chem.* 2022 Apr 26; 2022:6721937.
18. Haywood VB. Nightguard vital bleaching: current concepts and research. *J Am Dent Assoc.* 1997 Apr;128 Suppl:19S-25S.
19. Jyothi KS, Seshagiri M. In-vitro activity of saponins of *Bauhinia purpurea*, *Madhuca longifolia*, *Celastrus paniculatus*, and *Semecarpus anacardium* on selected oral pathogens. *J Dent (Tehran).* 2012;9(4):216-23.
20. Kablan H, Artık N, Karasu S, Tekin ZH, Sağdıç O, Cankurt H. The effect of Gypsophila extract as natural emulsifier on the steady, dynamic rheological behavior and microstructural properties of the ice cream mix. *Avr Bilim ve Teknol Derg.* 2022; 38:1-7.
21. Kang SH, Song WS, Shin KC, Oh DK. Preparation of in vivo intermediate metabolites of soybean saponins with improved bioactivity by in vitro deacetylation and deglycosylation. *Food Chem.* 2024; 460:140589.
22. Kareem O, Ali T, Dar LA, Mir SA, Rashid R, Nazli N, Gulzar T, Bader G. Positive health benefits of saponins from edible legumes: Phytochemistry and pharmacology. In: *Edible Plants in Health and Diseases: Volume II: Phytochemical and Pharmacological Properties.* 2022. p. 279-98.
23. Kaymak S, Kurtur OB, Gok B, Budama-Kilinc Y, Kecel-Gunduz S, Nath EÖ, Kartal M. Development of phytotherapeutic nanoformulation containing *Gypsophila eriocalyx* and its evaluation as a candidate formulation for osteoporosis treatment on human bone marrow stem cells. *Phytochem Anal.* 2024 Aug 26. doi: 10.1002/pca.3440. Epub ahead of print.
24. Khan MA, Zafaryab M, Mehdi SH, Ahmad I, Rizvi MMA. Characterization and anti-proliferative activity of curcumin loaded chitosan nanoparticles in cervical cancer. *Int J Biol Macromol.* 2016; 93:242-53.
25. Kolsuz Ozcetin H, Surmelioglu D. Effects of bleaching gel containing TiO₂ and chitosan on tooth surface roughness, microhardness and colour. *Aust Dent J.* 2020;65(4):269-77.
26. Koyuncu M, Kılıç CS, Güvenç A. Soaproot yielding plants of East Anatolia and their potential in nature. *Turk J Bot.* 2008;32(6):489-94.
27. Manne AA, Kumar A, Mangamuri U, Podha S. *Pterocarpus marsupium* Roxb. heartwood extract synthesized chitosan nanoparticles and its biomedical applications. *J Genet Eng Biotechnol.* 2020;18(1):19.
28. Meireles SS, Heckmann SS, Leida FL, dos Santos Ida S, Della Bona A, Demarco FF. Efficacy and safety of 10% and 16% carbamide peroxide tooth-whitening gels: a randomized clinical trial. *Oper Dent.* 2008;33(6):606-12.
29. Münchow EA, Hamann HJ, Carvajal MT, Pinal R, Bottino MC. Stain removal effect of novel papain - and bromelain-containing gels applied to enamel. *Clin Oral Investig.* 2016;20(8):2315-2320.
30. Oleszek WA. Chromatographic determination of plant saponins. *J Chromatogr A.* 2002;967(1):147-62.
31. Oluwasina OO, Ezenwosu IV, Ogidi CO, Oyeyayo VO. Antimicrobial potential of toothpaste formulated from extracts of *Syzygium aromaticum*, *Dennettia tripetala* and *Jatropha curcas* latex against some oral pathogenic microorganisms. *AMB Express.* 2019;9(1):20. doi:10.1186/s13568.019.0744-2.
32. Oluwasina OO, Idris SO, Ogidi CO, Igbe FO. Production of herbal toothpaste: Physical, organoleptic, phyto-compound, and antimicrobial properties. *Heliyon.* 2023;9(3).
33. Özçelik H, Yıldırım B. Türkiye çövenlerinin (*Gypsophila L.* ve *Ankyropetalum Fenzl spp.*) ekonomik önemi, kullanım olanakları ve korunması üzerine düşünceler. *SDÜ Orman Fak Derg.* 2011;12:57-61.
34. Patra JK, Das G, Fraceto LF, Campos EVR, Rodriguez-Torres MDP, Acosta-Torres LS, Diaz-Torres LA, Grillo R, Swamy MK, Sharma S, Habtemariam S, Shin HS. Nano based drug delivery systems: recent developments and future prospects. *J Nanobiotechnology.* 2018 Sep 19;16(1):71.
35. Paul TJ, Taylor TA, Rajendra Santosh AB. The potential of saponin from Jamaica's *Blighia sapida* (ackee) as a substitute for sodium lauryl sulphate in toothpaste. *Med Hypotheses.* 2020;137:109555. doi:10.1016/j.mehy.2020.109555.
36. Peniche H, Peniche C. Chitosan nanoparticles: a contribution to nanomedicine. *Polym Int.* 2011;60(6):883-9.
37. Pini NIP, Piccelli MR, Vieira-Junior WF, Ferraz LN, Aguiar FHB, Lima DANL. In-office tooth bleaching with chitosan-enriched hydrogen peroxide gels: in vitro results. *Clin Oral Investig.* 2022;26(1):471-479. doi: 10.1007/s00784.021.04021-4. Epub 2021 Jun 12.
38. Rajamanickam G, Manju S. Formulation and characterization of chitosan nanoparticles loaded with neuroprotective flavonoid from *Phyllanthus niruri* Linn. *Macromol Res.* 2023;31(1):13-24.
39. Rodrigues JA, Marchi GM, Ambrosano GM, Heymann HO, Pimenta LA. Microhardness evaluation of in situ vital bleaching on human dental enamel using a novel study design. *Dent Mater.* 2005;21(11):1059-67.
40. Sugianti N. Effect extract rosella (*Hibiscus sabdariffa*) as an alternative to natural tooth bleaching agent on external discoloration case. *Insisiva Dent J.* 2012;1(2).

41. Simunkova H, Pessenda-Garcia P, Wosik J, Angerer P, Kronberger H, Nauer GE. The fundamentals of nano- and submicro-scaled ceramic particles incorporation into electrodeposited nickel layers: zeta potential measurements. *Surf Coat Technol.* 2009;203(13):1806-14.
42. Soltanzadeh M, Peighambardoust SH, Ghanbarzadeh B, Mohammadi M, Lorenzo JM. Chitosan Nanoparticles as a Promising Nanomaterial for Encapsulation of Pomegranate (*Punica granatum L.*) Peel Extract as a Natural Source of Antioxidants. *Nanomaterials (Basel)*. 2021 May 29;11(6):1439.
43. Sun W, Mao S, Wang Y, Junyaprasert VB, Zhang T, Na L, Wang J. Bioadhesion and oral absorption of enoxaparin nanocomplexes. *Int J Pharm.* 2010 Feb 15;386(1-2):275-81. doi: 10.1016/j.ijpharm.2009.11.025. Epub 2009 Dec 1. PMID: 19958824.
44. Timilsena YP, Phosanam A, Stockmann R. Perspectives on saponins: Food functionality and applications. *Int J Mol Sci.* 2023;24(17). doi:10.3390/ijms241713538.
45. Upadhyay M, Hosur RV, Jha A, Bharti K, Mali PS, Jha AK, Mishra B, Kumar A. Myricetin encapsulated chitosan nanoformulation for management of type 2 diabetes: Preparation, optimization, characterization and in vivo activity. *Biomater Adv.* 2023 Oct; 153:213542.